



For Detail and  
EXCEPTIONAL FINISHINGS

SPECIFICATION SHEET

TRUPAN Standard MDF is a versatile product that will fit most general industrial uses including cabinets, fixtures and furniture components. An advanced refining process ensures a homogenous panel that is ideal for deep detailed profiling and finishing with exceptional performance results.

| TRUPAN STANDARD MDF   |          |                |                |                |                |                   |               |                  |                      |            |              |             |
|-----------------------|----------|----------------|----------------|----------------|----------------|-------------------|---------------|------------------|----------------------|------------|--------------|-------------|
|                       |          | Moncure, NC    |                |                |                | Bennettsville, SC |               |                  | Sault Ste. Marie, ON |            |              |             |
| Thickness Range       | (in./mm) | 1/4" - 0.35"   | 0.36" - 7/16"  | 1/2" - 3/4"    | 7/8" - 1"      | 3/8" - 13/16"     | 7/8" - 1 1/8" | 1 3/16" - 1 1/2" | 6mm - 8mm            | 9mm - 1/2" | 9/16" - 7/8" | 1" - 1 1/4" |
| Average MOR           | (psi)    | 4,205          | 3,915          | 3,915          | 3,915          | 4,000             | 4,000         | 4,000            | 4,200                | 3,100      | 3,100        | 3,800       |
| Average MOE           | (psi)    | 449,500        | 449,500        | 449,500        | 449,500        | 500,000           | 500,000       | 500,000          | 450,000              | 400,000    | 420,000      | 480,000     |
| Average Internal Bond | (psi)    | 160            | 138            | 109            | 102            | 100               | 90            | 85               | 175                  | 120        | 110          | 110         |
| Face Screw Hold       | (lb)     | 300            | 270            | 275            | 275            | 250               | 250           | 275              | N/A                  | 300        | 250          | 275         |
| Edge Screw Hold       | (lb)     | NA             | 225            | 225            | 225            | 225               | 175           | 225              | N/A                  | N/A        | 245          | 250         |
| Thickness Tolerance   | (in.)    | +/- .005       | +/- .005       | +/- .005       | +/- .005       | +/- .005          | +/- .005      | +/- .005         | +/- .005             | +/- .005   | +/- .005     | +/- .005    |
| Length and Width      | (in.)    | +/- 0.08       | +/- 0.08       | +/- 0.08       | +/- 0.08       | +/- 1/16          | +/- 1/16      | +/- 1/16         | +/- 1/16             | +/- 1/16   | +/- 1/16     | +/- 1/16    |
| Squareness            | (in.)    | <0.036" / foot | <0.036" / foot | <0.036" / foot | <0.036" / foot | +/- 1/8           | +/- 1/8       | +/- 1/8          | +/- 1/8              | +/- 1/8    | +/- 1/8      | +/- 1/8     |

|                       |          | Eugene, OR  |               |               | Malvern, AR |               |             |                 |
|-----------------------|----------|-------------|---------------|---------------|-------------|---------------|-------------|-----------------|
| Thickness Range       | (in./mm) | 3/8" - 15mm | 5/8" - 13/16" | 7/8" - 1 1/4" | 3/8" - 1/2" | 15mm - 11/16" | 18mm - 28mm | 1-1/8" - 1-1/2" |
| Average MOR           | (psi)    | 3,200       | 3,200         | 3,000         | 3,500       | 3,500         | 3,500       | 3,500           |
| Average MOE           | (psi)    | 300,000     | 300,000       | 300,000       | 350,000     | 350,000       | 350,000     | 350,000         |
| Average Internal Bond | (psi)    | 95          | 95            | 90            | 100         | 95            | 90          | 85              |
| Face Screw Hold       | (lb)     | 260         | 260           | 250           | 300         | 300           | 285         | 275             |
| Edge Screw Hold       | (lb)     | N/A         | 210           | 200           | N/A         | 225           | 225         | 225             |
| Thickness Tolerance   | (in.)    | +/- .005    | +/- .005      | +/- .005      | +/- .005    | +/- .005      | +/- .005    | +/- .005        |
| Length and Width      | (in.)    | +/- 1/16    | +/- 1/16      | +/- 1/16      | +/- 1/16    | +/- 1/16      | +/- 1/16    | +/- 1/16        |
| Squareness            | (in.)    | +/- 1/8     | +/- 1/8       | +/- 1/8       | +/- 1/8     | +/- 1/8       | +/- 1/8     | +/- 1/8         |

- The above physical properties are based on target averages of individual production lots. Sampling for conformance to the above specifications must be done in accordance with the procedures described in the American National Standard for MDF. (ANSI A208.2 – 2016 section 6.2 Sampling for Acceptance)
- EPA TSCA Title VI certified – TPC 1.
- Complies with formaldehyde emission requirements in MDF for CAN/CSA-0260-16, CPA-ECC-2011, ANSI 208.2-2016, and CCR 93120 (CARB Composite Wood ATCM Phase II).
- All panels are approved for interior, non-structural application.
- Contains Recycled/Recovered wood content.

Storage and Handling

TRUPAN MDF products should never be stored or used outdoors. The indoor storage area should be clean, dry, well ventilated, and free of dust, dirt or particles that could contaminate the particleboard. Store flat on stickers on a level, hard, dry surface. Constant relative humidity and temperature should be maintained. Before use, allow to stabilize to the same conditions as are expected after the panel is installed. Condition 48 to 72 hours prior to lamination. For more information, see Composite Panels Association Technical Bulletin: Storage and Handling of Particleboard and MDF.

California Proposition 65 Requirement:

Warning: Drilling, sawing, sanding or machining wood products generates wood dust, a substance known to the State of California to cause cancer. Avoid inhaling wood dust or use a dust mask or other safeguards for personal protection.



renewables  
for a  
better life

arauco

proudly supplied by

